



Meltem Kimya ve Tekstil İth. İhr. San. ve Tic. Ltd. Şti.
Pet Resin, Plasticers & PVC Floor Covers

Adana- Turkey

rev: 01
15.06.2013

MELFLEX PLASTICISER DOTP-H (DIOCTYL TEREPHTHALATE)

PARAMETER	VALUE	METHOD
MOLECULAR WEIGHT	390,57	
FORMULA	$C_{24}H_{38}O_4$	
FORM	LIQUID	
COLOR (Pt-Co Scale)	Max.60	ASTM D1045-08(1209)
ESTER CONTENT (GC-MS) (%)	Min.99,8	ASTM D3465
ACIDITY (as phthalic acid - wt %)	0,02 (± 0,01)	ASTM D1045-08
SPECIFIC GRAVITY @ 20°C (g/cm ³)	0,980 (±0,005)	ASTM D1045-08(D287-D4052)
REFRACTIVE INDEX (n ^D 20)	1,4895 (± 0,001)	ASTM D1045-08(D1218)
VISCOSITY @25°C (cP)	60 (± 10)	BROOKFIELD METHOD
WATER CONTENT (KARL FISHER)	NONE	ASTM D1045-08(E203)
FREEZING POINT (°C)	-48	
BOILING POINT @ 760 mm Hg (°C)	400	
OPEN CUP FLASH POINT (°C)	218 (± 3)	ASTM D-92
VAPOR PRESSURE (%)	217 (1,33mbar)	
VOLATILE SUBSTANCES (%)3hours at 125°C	Max. 0,5	ILL 003/1-04-48

Operating with:

ISO 9001-2000
ISO 14001
OHSAS 18001-2004
TSE

Approved by:

Mr.Ibrahim Soylemez

Address:

Hacı Sabancı Organize Sanayi Bölgesi
İstiklal Cad. No11
Adana 01351,Turkey
www.meltemkimya.com.tr