

TECHNICAL DATA SHEET**MELPET**[®] 32101

Properties	Value	Unit	Test Method
Intrinsic Viscosity	0,570 ± 0,02	dL/g	ASTM D4603
Color L*	84,0 ± 4,0		ASTM D6290
Color b*	-3,0 ± 1,0		ASTM D6290
Melting Point	250 ± 5	°C	ASTM D3418
Carboxylic End Group	30 ± 10	Eq/Ton	Titration Method
Bulk Density	0,88 ± 0,05	g/cm ³	ASTM D1895
Moisture Content	≤ 0,2	%	ASTM 6980
Chip Size	1,6 ± 0,2	g/100 chips	Weight Scale

DESCRIPTION AND APPLICATIONS:

MELPET[®] 32101 is crystalline, low molecular weight thermoplastic polymer made by continuous polymerization process followed by crystallization. **MELPET**[®] 32101 is especially formulated medical grade comply in European pharma requirements. This grade exhibits easy flow ability which benefits thin walled injection molding process.

MELPET[®] 32101 is especially suitable for the production of medical blood tubes.

MELPET[®] 32101 resin is considered safe for food packaging applications based upon compliance with FDA regulation 21 CFR Section 177.1630, European Legislation EU 10/2011 and RoHS Directive EU RoHS 3 (EU Directive 2015/863) amend with EU RoHS 2 (EU Directive 2011/65) and its subsequent amendments for heavy metal contents. This resin also complies with the requirements laid down in the European Pharmacopoeia (Ph. Eur.) 9th Edition, Supplement 9.8, Chapter 3.1.15.

PROCESSING CONDITIONS:

MELPET[®] 32101 has to be dried to moisture content below 30-40 ppm. The drying conditions typically used are 175°C for 6 hours; the dew point of the drying air should be at least -40 °C.

STORAGE AND HANDLING:

PET resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry with relative humidity below 50% and temperatures preferably don't exceed 50°C. MELTEM KİMYA would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PET within 6 months after delivery

Operating With: ISO 9001:2015 / ISO 14001:2015 / OHSAS 18001:2014

Meltem Kimya ve Tekst. San. İth. İhr. ve Tic. A.Ş.

Hacı Sabancı Organize Sanayi Bölgesi
İstiklal Cad. No:11 01351 Sarıçam, Adana/Türkiye
T : +90 322 394 52 20 F : +90 322 394 48 99
www.meltemkimya.com.tr