

TECHNICAL DATA SHEET

MELPET® TS760 - rPET

Properties	Value	Unit	Test Method
Intrinsic Viscosity	0,760 ± 0,02	dL/g	ASTM D4603
Acetaldehyde	≤ 1,0	ppm	ASTM F2013
Color L*	≥ 70		ASTM D6290
Color b*	≤ 10		ASTM D6290
Melting Point	240 ± 5	°C	ASTM D3418
Carboxylic End Group	25 ± 10	Eq/Ton	Titration Method
Bulk Density	0,88 ± 0,05	g/cm ³	ASTM D1895
Moisture Content	≤ 0,2	%	ASTM 6980
Chip Size	1,6 ± 0,2	g/100 chips	Weight Scale
Crystallinity	≥ 30	%	ASTM D3418

DESCRIPTION AND APPLICATIONS:

MELPET® TS760 - rPET is crystalline, high molecular weight thermoplastic polymer made by continues polymerization process followed by solid-state polymerization. This resin has produced from post-consumer-bottle flakes via glycolysis, which are the same origin of virgin PET.

MELPET® TS760 - rPET is especially formulated bottle grade PET for water applications. The resin offers excellent clarity, color, good strength characteristic and a low acetaldehyde content to minimize impact on aroma and flavor. Suitable for still water, edible oil and miscellaneous container applications.

MELPET® TS760 - rPET resin is considered safe for food packaging applications based upon compliance with FDA regulation 21 CFR Section 177.1630, European Legislation EU 10/2011 and RoHS Directive EU RoHS 3 (EU Directive 2015/863) amend with EU RoHS 2 (EU Directive 2011/65) and its subsequent amendments for heavy metal contents.

PROCESSING CONDITIONS:

MELPET® TS760 - rPET has to be dried to moisture content below 30-40 ppm. The drying conditions typically used are 175°C for 6 hours; the dew point of the drying air should be at least -40 °C.

STORAGE AND HANDLING:

PET resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry with relative humidity below 50% and temperatures preferably don't exceed 50°C. MELTEM KİMYA would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PET within 6 months after delivery

Operating With: ISO 9001:2015 / ISO 14001:2015 / OHSAS 18001:2014

Meltem Kimya ve Teks. San. İth. İhr. ve Tic. A.Ş.

Hacı Sabancı Organize Sanayi Bölgesi
İstiklal Cad. No:11 01351 Sarıçam, Adana/Türkiye
T : +90 322 394 52 20 F : +90 322 394 48 99
www.meltemkimya.com.tr